

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-149725

(43)Date of publication of application : 02.06.1998

(51)Int.Cl.

H01B 7/08

B32B 7/12

B32B 27/36

H01B 3/42

H01B 7/34

(21)Application number : 08-308287

(71)Applicant : SEKISUI CHEM CO LTD

(22)Date of filing : 19.11.1996

(72)Inventor : YAMAGUCHI BUNJI

TONO MASAKI

YAHARA KAZUYUKI

(54) FIRE-RESISTANT ADHESIVE FILM AND FLAT CABLE USING THIS FILM

(57)Abstract:

PROBLEM TO BE SOLVED: To provide the excellent adhesiveness and the excellent fire resistance by forming one surface of a board, which is made of thermoplastic polyester group resin, with an adhesive layer, which is formed of a thermoplastic polyolefin group resin and thermoplastic polyester, and forming this adhesive layer hard to burn.

SOLUTION: As a thermoplastic polyolefin group resin having heat melting property to be used for an adhesive layer, polypropylene group resin is used. As a thermoplastic polyester group resin having heat melting property to be used for an adhesive layer, polyethylene terephthalate is used. The polyolefin group resin improves the water resistance of the adhesive layer, and the polyester group resin improves the adhesiveness thereof between a film board. As a halogen group fire-resistance agent, in relation to the forming temperature of the thermoplastic polyester group resin, which forms the board, the halogen group fire-resistant agent, of which decomposing temperature is 250°C or more and of which halogen content is 20% or more, is desirable. In the case where content of the fire-resistant agent is small, fire-resistance is lowered, and in the case where the content thereof is large, adhesive strength is lowered.

## LEGAL STATUS

[Date of request for examination]

20.05.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration] withdrawal  
[Date of final disposal for application] 31.03.2004  
[Patent number]  
[Date of registration]  
[Number of appeal against examiner's decision of rejection]  
[Date of requesting appeal against examiner's decision of rejection]  
[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平10-149725

(43) 公開日 平成10年(1998) 6月2日

(51) Int.Cl. <sup>6</sup>	識別記号	F I	
H 0 1 B	7/08	H 0 1 B	7/08
B 3 2 B	7/12	B 3 2 B	7/12
	27/36		27/36
H 0 1 B	3/42	H 0 1 B	3/42
	7/34		7/34
			F
			B
		審査請求	未請求 請求項の数 5 O L (全 9 頁)

(21) 出願番号 特願平8-308287

(22) 出願日 平成8年(1996)11月19日

(71) 出願人 000002174

積水化学工業株式会社

大阪府大阪市北区西天満2丁目4番4号

(72) 発明者 山口 文治

大阪府三島郡島本町百山2-1 積水化学工業株式会社内

(72) 発明者 戸野 正樹

大阪府三島郡島本町百山2-1 積水化学工業株式会社内

(72) 発明者 矢原 和幸

大阪府大阪市北区西天満2-4-4 積水化学工業株式会社内

(54) 【発明の名称】 難燃性接着フィルム及びそれを用いたフラットケーブル

(57) 【要約】

【課題】 接着性及び電気絶縁性に優れると共に、難燃性の付与された難燃性多層フィルム及びそれを用いたフラットケーブルを提供する。

【解決手段】 熱可塑性ポリエステル系樹脂 (a) からなるフィルム基材上に、熱融着性を有する熱可塑性ポリオレフィン系樹脂 (b) 及び熱融着性を有する熱可塑性ポリエステル系樹脂 (c) からなる接着剤層が形成された難燃性接着性フィルムであって、上記基材及び／又は接着剤層が難燃剤により難燃化されている。